

MCI®-2026 Primer HS

PRODUCT DESCRIPTION

MCI-2026 Concrete Primer HS coating is a proprietary water-based, 2-component, epoxy coating system that outperforms and outlasts most solvent-based sealer systems without the associated odors, flammability, or VOC's. MCI-2026 Concrete Primer HS coating meets all of the USDA guidelines for use in federally inspected poultry and meat plants. MCI-2026 Concrete Primer HS coating is available in clear and can be colored using MCI-2026 HPCS colorants. MCI-2026 Concrete Primer HS coating can be used as a part of MCI-2026 flooring system or as a top coat.

RECOMMENDED USES

MCI-2026 Concrete Primer HS is the recommended primer for most MCI-2026 Flooring Systems. It is also recommended as a stand alone coating in areas that are subjected to medium to heavy traffic and moderate chemical spillage.

FEATURES

- Waterborne
- Solvent-free
- Odorless
- Fast drying time
- Easy Mixing Ratio
- Applies to damp concrete
- VOC compliant
- Moderate chemical resistance
- Good abrasion resistance
- Eliminates concrete dust
- Excellent adhesion
- No induction time
- Good mar resistance
- Cleans easily

COVERAGE

This product should be applied at the rate of approximately 250-350 sq. ft per gallon (6.14-8.60m²/l), which is between 6.4 to 4.6 wet mils (163-116.84 μm wet). As with all coatings, coverage is dependent on the smoothness and porosity of the surface. As a primer, the coverage rate should be 250 sq.ft. per gallon (6.14m²/l).

SURFACE PREPARATION

The substrate must be clean, dry, and sound with new concrete cured for at least 30 days at 70°F (21°C). Remove dust, laitance, grease, curing compounds, waxes, foreign particles, disintegrated or soft base materials, and any previously applied potentially incompatible coatings. Create a surface profile on concrete by either steel shot blasting or acid etching.

FOR BEST RESULTS

- For interior use only
- New concrete must cure for at least 30 days at 70°F (21°C)
- Do not thin the MCI-2026 Concrete Primer HS coating
- Do not use when Humidity Exceeds 70% indoors
- Do not allow material to puddle during application
- Allow each coat to dry tack-free before recoating
- Allow each coat within 24 hours of previous coat
- Discard any material subjected to freezing
- Do not apply to structurally unsound surfaces
- Do not apply heavier than recommended wet film thickness
- Apply a test patch to ensure adhesion to old paint

MIXING

Avoid mixing and application of this product if the floor temperature is below 55°F (13°C) or above 85°F (29°C). Also avoid application if the humidity is higher than 70% R.H. or lower than 25%. The temperature of the floor, materials and air in the area of the installation all play a role in how the product will apply and cure.

For 3/4 gallon (2.8L) and 3 gallon (11.36L) units: carefully pour entire contents of Part B container into Part A container. Do not change the ratio of A and B. Blend thoroughly for 3 to 5 minutes with a spiral mixing blade attached to a low-speed (400-600 rpm) electric drill. Take care not to induce air into the material when mixing. This will cause bubbles in the coating when applied.



For bulk units: portion out 2 gallons (7.57L) of Part A and 1 gallon (3.785L) of Part B into a clean 5 gallon (19L) pail. Blend in accordance with directions stated above.

APPLICATION

The recommended application of this product involves pouring it in a narrow line directly onto the concrete surface and then spreading it with a squeegee. Spread the coating in a continuous manner from one side of the area being coated to the other. Immediately follow with a 3/8" (0.95cm) nap shed resistance roller. The MCI-2026 Concrete Primer HS coating must be rolled as evenly as possible. To do this, roll forward in a straight line and then roll the same column backwards to eliminate spike shoe marks. Overlap the next column to be rolled by 1/2" (1.27 cm) with the previously rolled column. Avoid excess agitation of the liquids with the roller. This will lessen chances of bubbling of the final film.

POT LIFE

At 75°F (24°C) and 50% R.H. the MCI-2026 Concrete Primer HS has a useful working time or pot life of approximately 30-40 minutes. Using any product beyond this time will result in variable results and therefore any mixed product beyond the pot life should be discarded.

FOR INDUSTRIAL USE ONLY

KEEP OUT OF REACH OF CHILDREN

KEEP CONTAINER TIGHTLY CLOSED

NOT FOR INTERNAL CONSUMPTION

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

PHYSICAL PROPERTIES

Property	Typical Values
Shelf Life	2 years
Application Temperature and Humidity	55°F (13°C) to 85°F (29°C) at less than 70% R.H.
Mixing Ratio (A to B)	Clear: 2 to 1 by volume, 1.8 to 1 by weight Gray: 2 to 1 by volume, 2 to 1 by weight
Coverage	250-350 sq ft per gallon
Working Time	35 minutes at 75°F (24°C)
Application Method	Straight Squeegee and 3/8" Nap Roller
Ready for recoat	2-5 hours
Ready for Foot Traffic	7-12 hours
Ready for Heavy Traffic	24+ hours
Bond Strength	400+ psi w/ concrete failure (ASTM D-4541)
% Solids by volume	52% (ASTM D-1464)
Flash Point, PMCC	>200°F (93°C)
UV light Resistance	Good (QUV)
Hardness (Shore D)	80+ (ASTM D-2240)
VOC	11 g/l (EPA Method 24)
Gloss (60)	75 (50 Satin)
Impact Resistance	> 160 in-lbs (ASTM D-2794)
Indentation	None (MIL-D-3134F)
Abrasion Resistance	0.06 g (ASTM D-4060, CS-17 wheel)
Flammability	Self-Extinguishing (ASTM D-635)
Heat Resistance Limitation	140F (60C) Constant; 200F (93C) Intermittent
Water Absorption	0.2% (ASTM C-413)
Coefficient of Friction	0.77 (ASTM F-609)
Part A WPG	9.4-9.8 lb/gal (1.13-1.18 kg/l)
Part B WPG	8.5-8.8 lb/gal (1.02-1.05 kg/l)

PACKAGING

Size	Packaging	Ship Wt	Description
0.75 gal (2.8 L)	Small one batch unit	8.4 lbs (3.8 kg)	One hardener container and one resin container, packaged in a single carton
3.0 gal (11.36 L)	3 gallon kit	30 lbs (13.61 kg)	One bag of hardener and one bag of resin, packaged in a mixing/shipping pail, with tear strip lid
15.0 gal (56.8 L)	3 x 5 gal pail bulk unit	140 lbs (63.51 kg)	One 5 gal pail of hardener and Two 5 gal pails of resin
165.0 gal (624.5 L)	3 x 55 gal drum bulk unit	1600 lbs (725.87 kg)	One 55 gal drum of hardener and Two 55 gal drums of resin

LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



4119 White Bear Parkway, St. Paul, MN 55110 USA
Phone (651) 429-1100, Fax (651) 429-1122
Toll Free (800) 4-CORTEC, E-mail info@cortecvci.com
Internet <http://www.CortecVCI.com>

printed on recycled paper  100% post consumer
Revised 3/7/12, Cortec Corporation 2002-2012. All rights reserved. Supersedes: 12/7/06.

MCI® is a registered trademark of Cortec Corporation.
© 2012, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. ISO accreditation applies to Cortec's processes only.